

Pliolak AS 652 is a Solvent-based long-oil alkyd resin that provides good drying time, wrinkling resistance and weathering resistance, with good gloss and color retention.

Pliolak AS 652 is used for decorative coatings, including interior and exterior applications.

The 100% resin contains 65% oil and 23 % Phthalic Anhydride

Delivery form 75 % in Dearomatized White Spirit

For further information regarding this product please refer to:

Teresa Calvo Garcia

Tel: +34 944 711 500

eMail: teresa.calvo@synthomer.com

Property	Typical Value	Unit	Method ¹
Solids content	75.0	%	ISO 3251
Viscosity (Brookfield RVT #5/50 rpm @23 °C)	6500	mPas	ASTM D 1545
Acid value (on solid)	<10	mg KOH/g SC	ISO 2114
Color Index (Gardner)	<6		ISO 4630
Flash Point	42	°C	ISO 3679
Density (@20 °C)	0.97		ISO 2811-1

¹ internal method based upon the specified norm

Key Advantages

- Good applicability
- High gloss
- Good drying time
- Good wrinkling resistance
- Compatible with most long- and medium-oil alkyd resins
- 2010 VOC compliant

Shipping and Storage

To ensure maximum stability and optimum resin properties, resin should be stored in closed containers at temperature between 5°C and 25°C and away from heat sources and sunlight. All storage should conform to local fire and building codes. Steel drums and IBC should be stored away from all sources of flame or combustion. When properly stored, resin will remain stable for 12 months from the date of manufacture.

Product Safety

Before handling, please read the Safety Data Sheet of this product for advice on safety, use and disposal.