

Pliolak AU 620 is a Solvent-based long-oil urethane alkyd resin for decorative and marine coatings.

Pliolak AU 620 provides improved drying time and hardness as well as high resistance to abrasion and saponification.

The 100% resin contains 62% oil and 12 % Phthalic Anhydride

Delivery form 60 % in solvent D40

For further information regarding this product please refer to:

Teresa Calvo Garcia

Tel: +34 944 711 500

eMail: [teresa.calvo@synthomer.com](mailto:teresa.calvo@synthomer.com)

Property	Typical Value	Unit	Method <sup>1</sup>
Solids content	60.0	%	ISO 3251
Viscosity (Gardner @25 °C)	22.3	Stokes	ASTM D 1545
Acid value (on solid)	<10	mg KOH/g SC	ISO 2114
Color Index (Gardner)	<8		ISO 4630
Flash Point	37	°C	ISO 3679
Density (@20 °C)	0.92		ISO 2811-1

<sup>1</sup> internal method based upon the specified norm

## Key Advantages

- Improved drying time
- Improved hardness
- High resistance to abrasion and saponification
- Compatible with most medium and long-oil alkyd resins
- VOC 2010 compliant in combination with other resins

## Shipping and Storage

To ensure maximum stability and optimum resin properties, resin should be stored in closed containers at temperature between 5°C and 25°C and away from heat sources and sunlight. All storage should conform to local fire and building codes. Steel drums and IBC should be stored away from all sources of flame or combustion. When properly stored, resin will remain stable for 12 months from the date of manufacture.

## Product Safety

Before handling, please read the Safety Data Sheet of this product for advice on safety, use and disposal.