

REVACRYL L 3783 is an anionic stabilised aqueous dispersion of a styrene-acrylic copolymer.

For further information regarding this product please refer to:

Jeaneta Zieglerova

Tel: +420 737 206 966

eMail: Jeaneta.Zieglerova@synthomer.com

REVACRYL L 3783 is suitable for a wide range of interior and exterior wall applications.

Property	Typical Value	Unit	Method ¹
Solid content	50	%	ISO 3251
pH	8.0		ISO 976
Viscosity (Brookfield S2/50)	475	mPa.s	ISO 2555
MFFT	19	°C	ISO 2115
Tg	19	°C	internal method

¹ internal method based upon the specified norm

Key Advantages

- Good water and alkali resistance
- Excellent compatibility with pigments and extenders
- High binding power for pigments
- Robustness

Shipping and Storage

This product is supplied in road tankers or in non-returnable plastic drums secured by a lid with clamping ring or in non-returnable palletized bulk containers (net volume 1.000 lt). The product must be protected from frost and exposure to direct sunlight. Storage temperatures between +5 °C and +30 °C are recommended. The product contains in-can preservation to protect it against microbiological attack during transportation. For protection against microbiological contamination during storage stringent plant hygiene is essential. Depending on the storage conditions addition of suitable preservatives may be necessary. Care must be taken that drums and containers are properly closed. During storage, shipping and handling contact with metal surfaces that are not corrosion protected must be avoided. When stored properly, the product has a shelf life of 6 months from the date of delivery.

Product Safety

Before handling, please read the Safety Data Sheet of this product for advice on safety, use and disposal.