

Revacryl P 7693 is a water-based dispersion based on acrylic acid esters and styrene, APEO and ammonia free.

Revacryl P 7693 is a new generation binder specially developed for the formulation of high PVC interior paints.

It may also be used to manufacture Exterior paints.

For further information regarding this product please refer to:

Teresa Calvo Garcia

Tel: +34 944 711 500

eMail: teresa.calvo@synthomer.com

Property	Typical Value	Unit	Method ¹
Solids Content	50.0	%	ISO 3251
pH	8.3		ISO 976
Viscosity [Brookfield RVT #3, 20 rpm @23°C]	3000	cps	ISO 2555
Minimum Film Forming Temperature	19	°C	ISO 2115

¹ internal method based upon the specified norm

Key Advantages

- Superior binding power
- Ammonia free
- Excellent humid scrub resistance

Shipping and Storage

This product is supplied in road tankers or in non-returnable plastic drums secured by a lid with clamping ring or in non-returnable palletized bulk containers (net volume 1.000 lt). The product must be protected from frost and exposure to direct sunlight. Storage temperatures between +5 °C and +30 °C are recommended. The product contains in-can preservation to protect it against microbiological attack during transportation. For protection against microbiological contamination during storage stringent plant hygiene is essential. Depending on the storage conditions addition of suitable preservatives may be necessary. Care must be taken that drums and containers are properly closed. During storage, shipping and handling contact with metal surfaces that are not corrosion protected must be avoided. When stored properly, the product has a shelf life of 6 months from the date of delivery.

Product Safety

Before handling, please read the Safety Data Sheet of this product for advice on safety, use and disposal.