

Hydrophobic acrylate copolymer for the formulation of waterproof coatings and binders

For further information regarding this product please refer to:

Johnny Martin

Tel: 1-803-377-2208 | Mobile: 1-704-473-5471
eMail: johnny.martin@synthomer.com

Property	Typical Value	Unit	Method ¹
Chemistry Type	stearylated polymer		
Solids Content	40	%	EN ISO 3251
pH Value	9.0		DIN ISO 976
Ionic Character	anionic		
Color	white		intern
Viscosity (LVT #2@100rpm, 25°C)	45	mPa s	ISO 1652
Density	8.3	lb/gal	

¹ internal method based upon the specified norm

Application Advice

Sequapel 409 water-based emulsion provides excellent water repellency and holdout properties to nonwovens and textiles, and acts as a sizing agent for paper and paperboard.

- Provides excellent water holdout
- Highly dilutable melamine
- Stable with all binder types, especially starches
- Excellent stability over wide temperature range

Application Notes:

- After completion of a run, clean the equipment that has been used for dilution, storage, filtering, pumping and spraying. Special care must be taken to properly clean nozzles and filter screens. Storage tanks and mixing equipment used for this product should be cleaned and sterilized at least every six months.

Shipping and Storage

This product is supplied in road tankers or in non-returnable plastic drums or in totes (IBC). The product must be protected from frost and exposure to direct sunlight. Storage temperatures between +5 °C and +30 °C are recommended. Care must be taken that drums and containers are properly closed. During storage, shipping and handling contact with metal surfaces that are not corrosion protected must be avoided. When stored properly, the product has a shelf life of 6 months from the date of delivery. - Mix the contents thoroughly before using. - This product is freeze-thaw stable; however, a recommended practice is to limit the number of cold cycles.

Product Safety

Before handling, please read the Safety Data Sheet of this product for advice on safety, use and disposal.