

Terpolymer designed for elastomeric modification of PVC and plastic goods

For further information regarding this product please refer to:

Dr. Cecile Mazard

Tel: +33 1 69 29 27 26

eMail: cecile.mazard@synthomer.com

| Property | Typical Value | Unit | Method ¹ |
|-----------------------|------------------|---------|---------------------|
| Physical Form | off-white powder | | |
| Average Particle Size | 0.5 | mm | |
| Density | 1.10 | g/ml | |
| Tg | -19 | °C | |
| Hardness | 50 | Shore A | |

¹ internal method based upon the specified norm

Application Advice

Sunigum P2100 is an elastomer used for PVC modification that requires good compression set and light color.

Key Features

- Resistant to heat and UV radiation
- Allow to make low compression set plasticized PVC formulations
- Resistant to oil-based fluids, solvents, animal fats
- Soft touch haptics

Typical Applications

- Window gaskets

Shipping and Storage

Available packaging: 20kg bags (poly) & 400kg big bags

The product must be stored in dry, well ventilated area. It is recommended to store in original packaging, away from direct source of heat and sunlight. Information on environmental and hazard data may be taken from the material safety data sheet.

Product Safety

Before handling, please read the Safety Data Sheet of this product for advice on safety, use and disposal.