

LIPOLAN F 2530F

Moulded foam products based on LIPOLAN F 2530F exhibit under usual ambient conditions a low indentation hardness with a low resilience, achieving a unique visco-elastic effect. LIPOLAN F 2530F is an aqueous dispersion of a styrene-butadiene copolymer with a high solids content. It is stabilised using an alkaline salt of fatty acids, which also provides a good foamability. LIPOLAN F 2530F does not contain any antioxidant.



For further information regarding this product please refer to:
Dr. Hahn, Sabine

Tel: +49 (0)2365-49-19617 , Fax: +49 (0)2365-49-2529
eMail: Sabine.Hahn@synthomer.com

Property	Value	Unit	Method ¹
Solids Content	66,0	%	ISO 124
Viscosity	< 2.200	mPa s	ISO 1409
Surface Tension	39,0	mN/m	ISO 1655
pH Value	10,4		ISO 976

¹ internal method based upon the specified norm

Application Advice & Processing

LIPOLAN F 2530F remains mechanically stable when complying with the storage conditions given below.

Vulcanised latex foam made using LIPOLAN F 2530F exhibits a very low resilience, having a so-called "visco-elastic" effect. Both tensile strength and elongation at break of the vulcanised latex allow a great flexibility of mould design. LIPOLAN F 2530F has to be vulcanised in a similar manner to natural rubber latex. In order to achieve an optimal quality level, rubber chemicals must be adapted to the compound formulation and manufacturing conditions. LIPOLAN F 2530F suits to Dunlop, Talalay and the non-gel process.

Shipping and Storage

LIPOLAN F 2530F is delivered in road tankers. Shipment in 1 ton containers (IBC) is also possible.

LIPOLAN F 2530F must permanently be protected against frost. The ideal storage temperature range is between + 5C and + 30 C. Exposure to temperatures above + 30 C or to direct sunlight for extended periods of time has to be avoided. Temperatures never must exceed + 40 C.

Complying with these storage conditions the dispersion has a shelf life of 6 months after delivery, when kept permanently and tightly closed. The pH value of the dispersion may decrease due to absorption of carbon dioxide from air. Dispersions having a pH lower than 10 should be readjusted to the initial value using an aqueous KOH solution of 5 % concentration. Material in broached containers should be used as soon as possible. In some cases, a slight drying of the surface or some cream formation cannot be excluded. Therefore the dispersion or the compound made of it should be stirred or mixed before use.

Product Safety

Before handling, please read the Safety Data Sheet of this product for advice on safety, use and disposal.

Revision: 4, 30.10.2014

Disclaimer: This information and any other advice or recommendations given or made by us (collectively "Information"), are provided in good faith and are not intended to, nor do they, constitute professional advice or services. Information is provided ?AS IS? and on an ?AS AVAILABLE? basis and without warranty. We do not warrant or accept responsibility for the accuracy, timeliness or completeness of the Information, or for the suitability of the Information for a particular purpose. We do not accept responsibility, and exclude all liability (including under any implied warranties), for any matters arising out of or in connection with your reliance on the Information (including as to infringement of third party intellectual property rights) to the fullest extent permitted by law. Any Information concerning any possible use or application of Synthomer products is given by us in good faith; we do not warrant the fitness of any Synthomer products for any particular purpose and it is entirely for you to satisfy yourself fully as to the suitability of Synthomer products for any particular purpose. Synthomer products are sold in accordance with Synthomer's standard terms and conditions of sale which are available from www.synthomer.com/tc.